

**95 µ Soft-PVC monomeric, white glossy**
**Technical Product Information**
**Grade Characteristics**

Description	<b>Self-adhesive monomeric soft-PVC, white glossy, 95 microns</b>
Application	Digital print vinyl for eco-solvent, solvent and UV-based inksystems
Certificates	<b>B1 flame retardant according to DIN 4102, part 1 applied on Steel-board.</b> <b>REACH conform, complies with the toys norm EN 71 part 3</b>
Recommended application temperature	min. + 10°C
Product application temperature	- 30 to + 80°C
Durability	3 years **
Shelf life at 23°C / 50% moisture	2 years in original boxes **
Dimensionstability ( FINAT 14)	*** adhered to steel , no shrinkage in cross direction (CD) in machine direction (MD) max. 0,2 mm

Physical Properties Facestock	Value	Unit	Norm
Caliper	95 ± 5	µm	ISO 534
Stretch at break MD	> 160	%	DIN EN ISO 527
Tear resistance MD	> 26	Mpa	DIN EN ISO 527

Physical Properties Adhesive	Value	Unit	Norm
Adhesion* R2 → Removable, clear	6 ±3	N/25mm	Finat 1
Adhesion* R2xg → Removable, grey	5 ±4	N/25mm	Finat 1
Adhesion* R3xg → Removable, grey	10 ±4	N/25mm	Finat 1
Adhesion* R3 → Removable, clear	10 ±4	N/25mm	Finat 1
Adhesion* P3 → Permanent, clear	14 ±6	N/25mm	Finat 1
Adhesion* P3xg → Permanent, grey	16 ±6	N/25mm	Finat 1
Adhesion* P4 → Super-Permanent, clear	18 ±6	N/25mm	Finat 1
*Average value			24h on Glass

Physical Properties Liner	Caliper EN ISO 20 534	Substance ISO 536
H14 siliconised Kraftliner	0,144mm	135g/m <sup>2</sup>
D18 siliconised Kraftliner, double-sided PE-coated	0,150mm	140g/m <sup>2</sup>
D17 siliconised Kraftliner, double-sided PE-coated, microstructured	0,180mm	145g/m <sup>2</sup>

**Guarantee**

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

\*\* Normal storage and handling conditions. 2-3 years inside and up to 3 months outside in middle-European climate conditions, unprinted.

**AMC AG Division Intercoat**  
Boschstr. 12  
D-24568 Kaltenkirchen

Telefon: +49-(0)4191-8005-0  
Telefax: +49-(0)4191-2450  
Internet: www.Intercoat.de




OFICINA CENTRAL  
Rotonda de Pitágo  
28806 - Alcalá de Henares (Madrid)  
Atención comercial: 910 138 978  
www.vzzcv