

**Polyolefin 90 µm white glossy**

Kraft paper, permanent

**ed90 H14 P6****Technical Product Information**F  
i  
l  
m**Grade characteristics**

<b>Description</b>	Polyolefin film, white glossy
<b>Application</b>	PVC-free print for digital graphics and signage
<b>Coating</b>	With topcoat for UV inks and latex inks for digital printing
<b>Approvals</b>	Complies with EU-Regulations: Packaging 94/62/EC; Heavy Metal, PBB and PBDE 2003/11; toys regulation EN71/part 3; free of phthalate
<b>Remarks</b>	REACH conform

Physical properties	Value	Unit	Test method
Caliper	90	µm	ISO 534
Stretch at break md	-	%	DIN 53455
Tear resistance md	-	N/mm <sup>2</sup>	ISO 1924/1

A  
d  
h  
e  
s  
i  
v  
e**Description**

Permanent adhesive P6:  
Copolymeric acrylates, solvent free, excellent resistance to UV-light and ageing.

Physical properties	Value	Unit	Test method
Adhesion P6 → permanent	14 +/- 6	N/25mm	FTM 1 24h. glass

L  
i  
n  
e  
r**Description**

Liner H14:  
135g/m<sup>2</sup>, chlorine free bleached Kraftliner

Physical properties	Value	Unit	Test method
Substance	135	g/m <sup>2</sup>	ISO 536
Caliper	136	µm	ISO 534

**Storage and application data**

Recommended processing temperature	min. + 5°C
Product application temperature	- 30° up to + 90°C
Life expectancy	2 years
Shelf life at 23°C / 50% r.h.	2 years in original packing *

**Warranty**

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

**AMC AG Division Intercoat**

Boschstr. 12  
D-24568 Kaltenkirchen

Telephone: +49-(0)4191-8005-0 E-Mail: info@intercoat.de  
Telefax: +49-(0)4191-2450 Internet: www.intercoat.de

\* specific handling and storage conditions have to be observed

Valid from 30.11.2020

Subject to alterations



OFICINA CENTRAL  
Rotonda de Pitágoras 1. Nave 303  
28806 - Alcalá de Henares (Madrid)  
Atención comercial: 910 138 978  
www.vzzcv.com